

Rigitone Joint Adhesive 63

SDS 28 Page 1 of 2

1 IDENTIFICATION OF THE SUBSTANCE OR PREPARATION AND COMPANY

Substance/ Preparation	Synthetic Resin Based Joint Filler
Adhesives	Rigitone Joint Adhesive 63
Manufacturer	British Gypsum Limited Head Office East Leake Loughborough Leics. LE12 6HX
Telephone	08705 456123

2 COMPOSITION/INFORMATION OF INGREDIENTS

Synthetic resin dispersion, filling Titanium Dioxide and inorganic materials in water.

3 HAZARDS IDENTIFICATION

These products are not classified as hazardous under CHIP 2000. Refer to Section 15 - Regulatory Information.

4 FIRST AID MEASURES

Inhalation	Administer fresh air, make the affected person comfortable and keep warm. Apply artificial respiration if breathing becomes irregular or ceases. In case of unconsciousness, lay the person supported on his or her side and get medical advice.
Skin Contact	Remove soiled and impregnated clothing. Wash the wet skin with soapy water and rinse thoroughly. Do not use solvents or dilutions.
Eye Contact	Keep the eyelids open and rinse for at least 10 mins thoroughly with clean running water and seek medical advice, if irritation persists.
Ingestion	Consult a doctor immediately in the case of ingestion. Keep the affected person still. Do not induce vomiting.

Please note should any symptoms persist obtain medical assistance.

5 FIRE FIGHTING MEASURES

The products are fire resistant, but packaging may burn. All fire extinguishers are suitable media, observing normal fire fighting procedures.

6 ACCIDENTAL RELEASE MEASURES**Personal Precautions.**

Sections 7 - Handling and Storage and 8 - Exposure/Protection. Take care as regards risk of slipping.

Environmental protection measures.

Do not allow the product to enter the drains. In case of pollution of rivers, lakes and liquid effluent piping, obey the local laws and inform the responsible authorities.

Cleaning/absorption measures

Absorb the spilled material by using absorbents (e.g. sand, sawdust, soil) and collect for disposal according to site requirements in the containers provided for this.

7 HANDLING AND STORAGE**HANDLING****Instructions regarding safe working**

Ensure adequate ventilation.

Instructions regarding fire and explosion protection

No special measures required.

STORAGE**Requirements of storage rooms and containers**

Keep the containers tightly sealed.

Carefully close any open containers and store upright to exclude spillage.

Instructions regarding combined storage

No special measures required.

Further storage conditions data

Always store in containers corresponding to original holders.

Obey the instructions on the label.

Protect against heat and direct sunlight.

Store in a frost-free dry environment.

8 EXPOSURE CONTROLS/PERSONNEL PROTECTION**Technical precautions**

Ensure good ventilation.

Personal protection

Skin Wear gloves to avoid prolonged or repeated contact.

Eyes Wear safety goggles to BS EN 166 when mixing or sanding, or when handling products overhead.



British Gypsum

9 PHYSICAL AND CHEMICAL PROPERTIES

Appearance:- Paste.
 Colour: See Label.
 Odour:- Typical of it's type.
 Ph:- ca. 8

Pour Point: N/A
 Boiling Point: 100°C
 Flash Point: > 100°C

Ignition Point:
 Lower Ignition Point: 410°C
 Upper Ignition Point: N/A

Explosive Limits:
 Lower Explosive Limit: 2.6 vol. %
 Upper Explosive Limit: 12.6 vol %

Density at 20°C ca. 1.6 g/cm³
 Solubility: Water-Soluble.
 Viscosity at 23°C 56-58 Pas at 45/rps
 Solvent Content: 2%

10 STABILITY AND REACTIVITY

No special physical conditions need to be avoided or restrictions regarding incompatible materials

11 TOXICOLOGICAL INFORMATION

No known toxicological effects.

Prolonged skin and eye contact should also be avoided.

12 ECOLOGICAL INFORMATION

Stable product with no known adverse environmental effects.

13 DISPOSAL CONSIDERATIONS

Dispose at an authorised landfill site in accordance with the Waste Management Licensing Regulations 1994.

14 TRANSPORT INFORMATION

Not classified as hazardous for transport.

15 REGULATORY INFORMATION

Not classified as hazardous under the Chemicals (Hazard, Information and Packaging for Supply) (Amendment) Regulations 2000 (CHIP 2000).

This Safety Data Sheet is prepared in accordance with the Approved Code of Practice - L62 "Safety data sheets for substances and preparations dangerous for supply" (2nd Edition).

16 OTHER INFORMATION

Sources of key data used to compile Safety Data Sheet:

The Control of Substances Hazardous to Health Regulations 1999 (COSHH).

Health & Safety Executive Guidance Note EH40 Occupational Exposure Limits (current edition).

Recommended uses - Rigitone Jointing products are used with Rigitone Plasterboards.

This information reflects typical values and is not a product specification.

No warranty is hereby expressed or implied.

Note to User:

This Safety Data Sheet does not constitute the users own workplace risk assessment, which is required under COSHH (The Control of Substances Hazardous to Health) Regulations 1999.

Gypframe, Gyproc, Glasroc, Thistle, Artec and Rawl are all registered trade names of BPB United Kingdom Limited. Iso wool is a registered trade name of British Gypsum-Isover Ltd, a joint venture between the insulation division of British Gypsum and Isover Saint-Gobain.

British Gypsum reserves the right to revise product specification without notice. The information given is correct to the best of our knowledge at the time of publication, but it is the users responsibility to ensure it remains current prior to use.

The enclosed information should not be read in isolation as it is meant only as guidance for the customer, who should always ensure that they are fully conversant with the products and systems being used and their subsequent installation prior to the commencement of a job. We advise that you read and familiarise yourself with all the information contained in this literature prior to the commencement of the work or specification. For further details refer to our Health and Safe Handling Data Sheet which is available on request.

For a comprehensive and up to date library of information visit our website at: www.british-gypsum.bpb.com

Technical enquiries
 British Gypsum Limited
 Drywall Academy Advice Centre
 East Leake
 Loughborough
 Leicestershire LE12 6JT

Telephone: 08705 456123
Followed by #1 (Literature), #2 (Specifiers), #3 (Merchants), #4 (Contractors)
Fax: 08705 456356
E-mail: bgtechnical.enquiries@bpb.com

Training enquiries 08702 406040



FM52358

© British Gypsum June 2002 SDS 28